

## Corrosion Resistance of individual materials

MEDIUM	Carbonstahl C 15 C 85	1.3505	1.3541 1.4028 1.4034	1.4301 1.4306	1.4401 1.4404
Natural Fats	A	A	A	A	A
Mineral Oils	A	A	A	A	A
Water	C	C	B	A	A
Saltwater	C	C	C	A	A
Hydrocarbon	B	B	A	A	A
Hydrochloric Acid	C	C	C	C	C
Sulfuric Acid	C	C	C	C	B
Nitric Acid	C	C	B	A	A
Alkaline Salts	C	C	B	A	A
General Foodstuff	C	C	B	A	A
Ammonia 30 %	B	B	C	A	A
Fruits / Vegetables	C	C	B	B	A
Benzene	A	A	A	A	A
Chlorinated Carbon Hydrogen	B	B	B	A	A
Caustic Soda	C	C	C	B	B
Ether	A	A	A	A	A

A = VERY RESISTANT    B = CONDITIONALLY RESISTANT    C = NOT RESISTANT